TDS

Technical Data Sheet

HARDENER

21-1 [Hardener for Wash Primmer]

1. GENERAL INFORMATION

Isocyanate for polyurethane paint system. It's provide good, reactivity with Acrylic polyol paint system. It's also provide good appearance, high gloss, good weathering resistance, after completed reaction.
Packing Size : -

2. MIXING

COMPONENTS
Follow the main product recommendations
APPLY VISCOSITY
Follow the main product recommendations

3. APPLICATION

Application : Follow the main product recommendations
This data relates only to the material designated herein and does not apply to use in combination with any other material or any process.
The data is not to be considered as a warranty or quality specification and assumes no liability in connection with its use.

5. PHYSICAL PROPERTIES

Specific Gravity : 0.87 - 0.89 g/cm^3

6. VOC REGULATION AREAS

These directions refer to the use of products which may be restrictors require special mixing instruction in VOC regulation areas. Follow mixing usage and recommendations in the VOC compliant products Chart for your area.

7. SAFETY AND HANDLING

For professional or trained applicator use only. Not for sale or use by the public. Before use, read and follow all TDS, label, and SDS precautions. Flammable product. Keep outreach of children. Always wear approved organic vapor goggles and a safety mask when using a product. Apply paint in good ventilating area.